


UNCLASSIFIED

SEP 10 1956




270 670

270 670

# TECHNICAL REPORT

## MATERIAL LABORATORY

NEW YORK NAVAL SHIPYARD  
BROOKLYN 1, NEW YORK



9ND-NYNS-800-P-1A

Reproduced From  
Best Available Copy



XEROX

62-21

19990329010

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

U N C L A S S I F I E D

RESEARCH REPORT  
on  
THE SPECTRAL REFLECTANCE AND TRANSMITTANCE  
OF STANDARD FABRICS FOR  
THERMAL RADIATION EFFECTS STUDIES

Lab. Project 5046-3, Part 71, Final Report  
NF 061-001  
Technical Objective A-7, AFSPF 957

28 Aug 1956

G. P. de Ihery  
W. Darksen  
T. I. Monahan

Optics and Nucleonics Branch  
J. M. McGreevy, Head

Superintending Engineer  
GEO. J. DASHEFSKY

The Director  
CAPTAIN A. B. JONES, Jr., USN

NAVAL MATERIAL LABORATORY  
New York Naval Shipyard  
Brooklyn 1, N. Y.

U N C L A S S I F I E D

#### SUMMARY

The spectral reflectance and transmittance of standard fabrics for thermal radiation research, varying in color from undyed to deep black, were measured for radiation of wave lengths from 0.40 to 2.7 microns. The spectral characteristics of white sheeting, olive green 107 cotton sateen, and wind resistant poplin, shade 116, were also measured. These standard cloths are being employed in the thermal radiation studies at NML and other laboratories. The reflectance for carbon-arc radiation of the standard fabrics ranged from 0.63 for the undyed sateens to 0.09 for the deep black. The carbon-arc radiant transmittances ranged from 0.12 for the undyed sateens to 0.00 for the dark gray, black and deep black. The radiant absorptances ranged from 0.25 for the undyed sateens to 0.91 for deep black.

TABLE OF CONTENTS

	Page No.
SUMMARY	2
ADMINISTRATIVE INFORMATION	4
INTRODUCTION	4
EXPERIMENTAL PROCEDURE	4
RESULTS	5
BIBLIOGRAPHY	7

TABLES

- 1 - The Spectral Transmittance And Reflectance Of The Standard Fabrics For Thermal Radiation Effects Studies
- 2 - The Spectral Transmittance And Reflectance Of The Uniform Fabrics
- 3 - The Carbon-arc and 3000°K Black-body Radiant Absorptance, Reflectance and Transmittance of the Standard Fabrics for Thermal Radiation Effects Studies

FIGURES

- 1 - The Spectral Transmittance of the Standard Fabrics for Thermal Radiation Effects Studies
- 2 - The Spectral Transmittance of the Uniform Fabrics
- 3 - The Spectral Reflectance of the Standard Fabrics For Thermal Radiation Effects Studies
- 4 - The Spectral Reflectance of the Uniform Fabrics
- 5 - The Spectral Absorptance of the Standard Fabrics for Thermal Radiation Effects Studies
- 6 - The Spectral Absorptance of the Uniform Fabrics

#### ADMINISTRATIVE INFORMATION

1. This investigation has been conducted at the Naval Material Laboratory as part of the program originally proposed by Commander, New York Naval Shipyard, confidential letter S99/15, Ser 960-22, of 15 March 1950 and approved by Bureau of Ships speedletter S99-(0)(340), Ser 340-75, of 6 April 1950. The Thermal Radiation studies at the Naval Material Laboratory are sponsored by the Armed Forces Special weapons Project. The reflectance and transmittance data of the standard fabrics were requested by Armed Forces Special Weapons Project letter, SWPEF-1 928 of 30 November, 1955 and the Quartermaster Research and Development Command letter, QMRDO-PRS of 30 November, 1955.

#### INTRODUCTION

2. A series of fabrics have been prepared by the Quartermaster Research and Development Command for use by the various agencies conducting thermal radiation effects studies under the sponsorship and coordination of the Armed Forces Special Weapons Project. These special fabrics consist of 9 oz./yd<sup>2</sup> cotton sateen dyed to various shades of gray with finely divided lampblack as a pigment and a methyl cellulose binder. Also included in the standard cloths were a light weight cotton sheeting and a poplin to be employed as component of the Hot-Wet uniform. The cloths were designated as follows:

- QM-1. cotton, sheeting, 4 oz., bleached.
- QM-2. cotton, sateen, 9 oz., prepared for dyeing.
- QM-3. cotton, sateen, 9 oz., O.G.107.
- QM-4. cotton, sateen, 9 oz., undyed, W/GMC.
- QM-5-65. cotton, sateen, 9 oz., GMC and carbon black, light gray.
- QM-6-40. cotton, sateen, 9 oz., GMC and carbon black, medium gray.
- QM-7-22. cotton, sateen, 9 oz., GMC and carbon black, dark gray.
- QM-8-12. cotton, sateen, 9 oz., GMC and carbon black, black.
- QM-9-7. cotton, sateen, 9 oz., GMC and carbon black, deep black.
- QA-RRS-1. cotton, W. R. Poplin, 5 oz., Type II, class A, shade 116.

3. For use in thermal radiation effect studies it is desirable to know the spectral reflectance and transmittance as well as the radiant absorptance, reflectance, and transmittance for the particular source employed. The Naval Material Laboratory has measured the spectral reflectance and transmittance for wave lengths from 0.40 to 2.7 microns and has computed the radiant absorptance, reflectance and transmittance for the carbon-arc and 3000 K black-body spectra.

#### EXPERIMENTAL PROCEDURE

4. The spectral reflectance and transmittance of special fabrics for thermal radiation studies were measured employing three spectrophotometers covering the wave length range from 0.40 to 2.7 microns. The data for the visible spectrum, from 0.40 to 0.70 micron, were obtained by the General Electric, dual beam, recording spectrophotometer. The near infra-red measurements, from 0.70 to 1.0 micron, were made with a similar spectrophotometer modified to measure longer wave lengths. The data for the infrared wave lengths from 1.0 to 2.7 microns, were measured employing a recording reflectometer, constructed at NML.<sup>1</sup>

---

#### Bibliography.

5. The data on the infrared reflectometer were extended to 0.50 micron so that correlation between the three measuring devices could be obtained.
6. In the visible and near infrared regions a vitrolite reflectance standard, which had been calibrated against a smoked magnesium oxide surface by the National Bureau of Standards, was employed. The absolute reflectance of vitrolite was computed from data for magnesium oxide published by Middleton.<sup>2</sup>
7. In the infrared region above 1.0 micron, an aluminized glass mirror was employed as a reference reflectance standard. The reflectance of the aluminized mirror for wave lengths less than 1.0 micron was measured on the O. E. Spectrophotometers, and values for the longer infrared wave lengths were extrapolated employing the data for aluminized films as published by Hass.<sup>3</sup>
8. When measuring transmittances for diffuse substances, in the visible and near infrared, a light baffle was employed inside the collecting sphere of the General Electric Spectrophotometer to block transmitted light that would be directly deflected to the receiving cell before reflection from the sphere wall. The fabric samples were placed against the port in the sphere wall rather than in the normal position for specular samples. The diffusely transmitted energy which failed to enter the sphere in the specular position could be as much as 50 per cent.

#### RESULTS

9. The spectral reflectance and transmittance for the standard fabrics are given in Tables 1 and 2. For ease of inspection the spectral transmittance is plotted, in Figure 1 for the grays and in Figure 2 for the uniform fabrics. The spectral reflectance is similarly plotted in Figures 3 and 4, and the absorptance in Figures 5 and 6.
10. As an indication of the reproducibility of the reflectances obtained with the instruments used at NML, it was determined that the reflectance of the olive green cotton sateen deviated no more than  $\pm 0.02$  from the samples of the 9 oz/yd<sup>2</sup> OG 107 cotton sateen investigated periodically during the past four years.
11. The transmittance of the three darkest grays, the deep black, the black and dark gray was found to be less than 0.005 for all wave lengths. The two outer uniform fabrics, the OG sateen and poplin, likewise did not transmit radiation in the visible and near infrared but for wave lengths longer than 1.0 micron the transmittance was as high as 0.11 for the sateen and as high as 0.23 for the lighter poplin. The light sheeting, intended for an underwear fabric, transmitted 0.36 non-selectively in the visible and near infrared regions; for wave lengths longer than 1.4 microns, however, the transmittance decreased irregularly to a minimum of 0.15 at 2.5 microns. The transmittance of the medium gray, light gray and undyed fabrics was about 0.01 at 0.4 micron and at 2.7 microns, with a maximum value in the region of 1.0 micron, dependent on the amount of dye added. The fabrics which transmit, do so selectively with wave length.

12. The reflectance of the darker gray fabrics gradually increases from its lowest value at 0.4 microns to a maximum about twice this value at approximately 2 microns, resulting in a selectivity to this extent. The lighter grays and undyed sateens show the typical irregular spectral reflectance of cotton fabrics in general, with a maximum value in the red and near infrared regions. The reflectance is influenced only for the visible radiation by the finely divided lampblack pigment. The uniform fabrics which were dyed olive green have a low reflectance in the visible region, the irregular reflectance varying from a low of 0.05 at 0.4 microns to a maximum of about 0.1 at 0.55 microns and decreasing again for the red wave lengths. The reflectance for the uniform fabric increases rapidly in the near infrared to values of 0.60 to 0.65 at about 1.3 microns and follows the reflectance characteristic of the undyed fabrics for the longer infrared wave lengths. The reflectance characteristic of having twice the reflectance for the green radiant energy than for the other colors imparts the green color to the fabric; the low reflectance results in the dark or olive green shade.


13. The spectral absorptance for the three darkest gray sateens is high and only slightly selective. The other fabrics have a wave length selectivity to thermal radiation which is important in most studies.

14. The radiant reflectance, transmittance and absorptance were computed for the carbon-arc and the tungsten spectra and are listed in Table 3. Also included in the table are the values for the fabrics with special absorption characteristics prepared similarly as the present standard thermal radiation fabrics. The absorptance of the standard fabrics range from 91 per cent for the deep black to 25 per cent for the undyed sateen. Table 3 illustrates that the effect of the spectral selectivity of the standard fabrics is small for the range of sources normally employed in laboratory studies of intense thermal radiation effects. The carbon-arc and 3000 K black body radiant absorptance reflectance and transmittance for the three uniform fabrics, the O.G. cotton sateen, the poplin and the bleached sheeting however are appreciably selective.

15. The three darkest grays have no net thermal radiation energy transmittance as determined from the spectrophotometric data; the other fabrics, however, all have some transmittance even though only the 4 oz/yd<sup>2</sup> sheeting has visible transmittance. The difference in radiant absorptance between the poplin and sateen uniform fabrics is due only to the difference in the amount of infrared energy transmitted.

16. Visual examination of the gray fabrics of recent fabrication compared to those made several years ago indicates that the color designations will cause confusion. This is borne out by the reflectance and absorptance of the "deep black" fabric which has less absorption than one previously called "dark gray". Considerable burn and other thermal effect data have been obtained with the earlier gray sateens which will be of value in studies with these fabrics if proper corrections are made. For precise reference to a fabric the actual absorptance would provide definite designation of the particular fabric.

Approved:

  
A. D. JONES, JR., CAPTAIN, USN  
The Director



BIBLIOGRAPHY

1. Naval Material Laboratory. An Automatic Recording Reflectometer for Measuring Diffuse Reflectance in the Visible and Infrared Regions, Lab. Project 5466 (Jan. 1955).
2. Middleton, W. E. K., Sanders, C.L., The Absolute Spectral Diffuse Reflectance of Magnesium Oxide, J. O. S. A., 41, 6. (June, 1951.).
3. Hass, George, Filmed Surfaces for Reflecting Optics, J.O.S.A., 45,11, November, 1955.
4. Naval Material Laboratory, Spectrophotometric Characteristics of Cloths, Lab. Project 5046-3 Part 66, (Oct. 1954).




FIGURE 1. THE SPECTRAL TRANSMITTANCE OF THE STANDARD FABRICS FOR THERMAL RADIATION EFFECTS STUDIES




FIGURE 2. THE SPECTRAL TRANSMITTANCE OF THE UNIFORM FABRICS




FIGURE 3. THE SPECTRAL REFLECTANCE OF THE STANDARD FABRICS  
FOR THERMAL RADIATION EFFECTS STUDIES




FIGURE 4. THE SPECTRAL REFLECTANCE OF  
THE UNIFORM FABRICS




FIGURE 5. THE SPECTRAL ABSORBANCE OF THE STANDARD FABRICS  
FOR THERMAL RADIATION EFFECTS STUDIES




FIGURE 6. THE SPECTRAL ABSORPTANCE OF THE UNIFORM FABRICS

TABLE 1  
The Spectral Transmittance and Reflectance of the  
Standard Fabrics for Thermal Radiation Effect Studies

Wave Length (microns)	Cotton Sateen Prepared for Dyeing (2)		Undyed Cotton Sateen (4)		Light Gray Cotton Sateen (5-65)		Medium Gray Cotton Sateen (6-10)		Dark Gray Cotton Sateen (7-22)		Black Cotton Sateen (8-12)		Deep Black Cotton Sateen (9-7)	
	R	T	R	T	R	T	R	T	R	T	R	T	R	T
0.40	0.42	0.02	0.47	0.02	0.42	0.02	0.42	0.01	0.16	0.00	0.09	0.00	0.07	0.00
0.42	0.46	0.03	0.50	0.04	0.44	0.02	0.44	0.02	0.17	0.00	0.09	0.00	0.07	0.00
0.44	0.49	0.04	0.53	0.05	0.46	0.03	0.45	0.02	0.17	0.00	0.09	0.00	0.07	0.00
0.46	0.52	0.05	0.56	0.06	0.48	0.03	0.46	0.02	0.18	0.00	0.09	0.00	0.07	0.00
0.48	0.55	0.07	0.59	0.07	0.50	0.04	0.47	0.02	0.18	0.00	0.09	0.00	0.07	0.00
0.50	0.58	0.08	0.61	0.09	0.51	0.04	0.47	0.02	0.18	0.00	0.10	0.00	0.07	0.00
0.52	0.60	0.09	0.63	0.10	0.52	0.05	0.48	0.02	0.19	0.00	0.10	0.00	0.07	0.00
0.54	0.63	0.11	0.65	0.11	0.54	0.05	0.49	0.03	0.19	0.00	0.10	0.00	0.08	0.00
0.56	0.65	0.12	0.67	0.12	0.55	0.06	0.49	0.03	0.19	0.00	0.10	0.00	0.08	0.00
0.58	0.67	0.13	0.68	0.13	0.55	0.06	0.50	0.03	0.19	0.00	0.10	0.00	0.08	0.00
0.60	0.68	0.14	0.70	0.14	0.56	0.06	0.50	0.03	0.20	0.00	0.10	0.00	0.08	0.00
0.62	0.70	0.15	0.71	0.15	0.57	0.07	0.51	0.03	0.20	0.00	0.10	0.00	0.08	0.00
0.64	0.71	0.16	0.71	0.16	0.57	0.07	0.51	0.03	0.20	0.00	0.10	0.00	0.08	0.00
0.66	0.72	0.17	0.72	0.17	0.58	0.08	0.51	0.04	0.20	0.00	0.11	0.00	0.08	0.00
0.68	0.73	0.18	0.73	0.18	0.59	0.08	0.52	0.04	0.21	0.00	0.11	0.00	0.08	0.00
0.70	0.73	0.19	0.74	0.18	0.57	0.08	0.50	0.04	0.21	0.00	0.11	0.00	0.08	0.00
0.75	0.72	0.19	0.72	0.19	0.58	0.09	0.51	0.03	0.20	0.00	0.10	0.00	0.08	0.00
0.80	0.74	0.19	0.74	0.19	0.60	0.09	0.53	0.03	0.21	0.00	0.11	0.00	0.09	0.00
0.85	0.74	0.20	0.73	0.19	0.60	0.10	0.53	0.03	0.21	0.00	0.11	0.00	0.09	0.00
0.90	0.74	0.20	0.74	0.19	0.60	0.10	0.54	0.03	0.22	0.00	0.11	0.00	0.09	0.00
0.95	0.74	0.19	0.73	0.19	0.61	0.10	0.54	0.03	0.22	0.00	0.11	0.00	0.09	0.00
1.00	0.74	0.20	0.73	0.19	0.60	0.10	0.54	0.03	0.22	0.00	0.11	0.00	0.09	0.00
1.10	0.72	0.19	0.71	0.19	0.61	0.11	0.54	0.04	0.23	0.00	0.12	0.00	0.10	0.00
1.20	0.71	0.17	0.70	0.17	0.61	0.10	0.54	0.04	0.24	0.00	0.12	0.00	0.10	0.00
1.30	0.71	0.18	0.71	0.18	0.62	0.11	0.56	0.04	0.25	0.00	0.13	0.00	0.10	0.00
1.40	0.68	0.15	0.66	0.15	0.62	0.10	0.56	0.04	0.26	0.00	0.14	0.00	0.11	0.00
1.50	0.54	0.06	0.54	0.05	0.51	0.05	0.50	0.02	0.25	0.00	0.13	0.00	0.11	0.00
1.60	0.56	0.07	0.56	0.06	0.53	0.06	0.50	0.02	0.25	0.00	0.14	0.00	0.11	0.00
1.70	0.63	0.11	0.63	0.11	0.58	0.08	0.55	0.03	0.27	0.00	0.14	0.00	0.12	0.00
1.80	0.61	0.10	0.61	0.10	0.58	0.07	0.55	0.03	0.27	0.00	0.14	0.00	0.12	0.00
1.90	0.58	0.09	0.58	0.09	0.57	0.07	0.54	0.03	0.28	0.00	0.15	0.00	0.13	0.00
2.00	0.55	0.07	0.54	0.06	0.52	0.06	0.51	0.03	0.27	0.00	0.15	0.00	0.13	0.00
2.10	0.41	0.02	0.40	0.01	0.41	0.02	0.41	0.01	0.25	0.00	0.15	0.00	0.13	0.00
2.20	0.48	0.04	0.48	0.03	0.47	0.03	0.47	0.02	0.26	0.00	0.15	0.00	0.13	0.00
2.30	0.42	0.02	0.39	0.01	0.39	0.02	0.39	0.01	0.24	0.00	0.15	0.00	0.12	0.00
2.40	0.39	0.02	0.40	0.01	0.40	0.02	0.39	0.01	0.25	0.00	0.15	0.00	0.13	0.00
2.50	0.30	0.01	0.29	0.00	0.29	0.01	0.32	0.01	0.21	0.00	0.14	0.00	0.12	0.00
2.60	0.36	0.01	0.36	0.01	0.36	0.01	0.37	0.01	0.24	0.00	0.15	0.00	0.12	0.00
2.70	0.34	0.01	0.35	0.01	0.34	0.01	0.36	0.01	0.16	0.00	0.13	0.00	0.12	0.00

R - reflectance  
T - transmittance



TABLE 2  
The Spectral Transmittance and Reflectance of  
the Uniform Fabrics

Wave Length (microns)	Bleached Cotton Sheeting (1)		Cotton Sateen O.G.107 (3)		Cotton Poplin Shade 116 (21S-1)	
	R	T	R	T	R	T
0.40	0.61	0.35	0.05	0.00	0.05	0.00
0.42	0.61	0.36	0.05	0.00	0.05	0.00
0.44	0.61	0.37	0.05	0.00	0.05	0.00
0.46	0.61	0.37	0.05	0.00	0.06	0.00
0.48	0.61	0.36	0.06	0.00	0.08	0.00
0.50	0.61	0.36	0.06	0.00	0.09	0.00
0.52	0.61	0.36	0.07	0.00	0.10	0.00
0.54	0.60	0.36	0.09	0.00	0.11	0.01
0.56	0.60	0.36	0.10	0.00	0.11	0.01
0.58	0.60	0.36	0.09	0.00	0.11	0.01
0.60	0.59	0.36	0.09	0.00	0.10	0.00
0.62	0.59	0.37	0.08	0.00	0.09	0.00
0.64	0.59	0.37	0.07	0.00	0.08	0.00
0.66	0.59	0.37	0.07	0.00	0.08	0.00
0.68	0.59	0.37	0.06	0.00	0.08	0.00
0.70	0.59	0.38	0.07	0.00	0.08	0.00
0.75	0.58	0.37	0.08	0.00	0.09	0.00
0.80	0.59	0.37	0.11	0.00	0.12	0.01
0.85	0.59	0.37	0.15	0.00	0.17	0.01
0.90	0.59	0.38	0.22	0.00	0.25	0.03
0.95	0.60	0.38	0.30	0.01	0.35	0.06
1.00	0.59	0.37	0.37	0.03	0.43	0.10
1.10	0.58	0.37	0.52	0.08	0.60	0.20
1.20	0.58	0.36	0.57	0.10	0.64	0.22
1.30	0.57	0.37	0.61	0.11	0.67	0.24
1.40	0.58	0.36	0.60	0.10	0.66	0.22
1.50	0.50	0.27	0.51	0.05	0.53	0.16
1.60	0.51	0.29	0.53	0.06	0.54	0.16
1.70	0.55	0.34	0.60	0.09	0.62	0.19
1.80	0.55	0.33	0.59	0.09	0.61	0.18
1.90	0.53	0.32	0.56	0.08	0.59	0.17
2.00	0.51	0.30	0.54	0.07	0.55	0.15
2.10	0.39	0.20	0.10	0.02	0.39	0.06
2.20	0.46	0.26	0.48	0.04	0.47	0.10
2.30	0.38	0.20	0.39	0.01	0.38	0.06
2.40	0.32	0.20	0.37	0.02	0.38	0.06
2.50	0.31	0.14	0.31	0.01	0.29	0.03
2.60	0.37	0.19	0.36	0.01	0.36	0.05
2.70	0.36	0.19	0.34	0.01	0.35	0.05

TABLE 3  
The Carbon-arc and 3000°K Black-body  
Radiant Absorptance, Reflectance and Transmittance  
of the Standard Fabrics for Thermal Radiation Effects Studies

QMRDL No.	QMRDL Color	Cloth	Carbon-arc Spectrum			3000°K Black-body		
			R	T	A	R	T	A
9-7	Deep Black	Cotton Sateen	0.09	0.00	0.91	0.10	0.00	0.90
8-12	Black	Cotton Sateen	0.11	0.00	0.89	0.12	0.00	0.88
7-22	Dark Gray	Cotton Sateen	0.21	0.00	0.79	0.23	0.00	0.77
6-40	Medium Gray	Cotton Sateen	0.50	0.02	0.47	0.51	0.03	0.46
5-65	Light Gray	Cotton Sateen	0.54	0.07	0.39	0.56	0.07	0.37
4	Undyed	Cotton Sateen	0.63	0.12	0.25	0.63	0.13	0.24
3	O.G. 107	Cotton Sateen	0.28	0.03	0.69	0.40	0.05	0.55
2	Prepared for Dying	Cotton Sateen	0.63	0.12	0.25	0.64	0.13	0.23
1	Bleached	Cotton Sheeting	0.58	0.34	0.08	0.54	0.33	0.13
RRS-I	Shade 116	Cotton Poplin	0.30	0.07	0.63	0.57	0.12	0.31
	Black	Cotton Sateen	0.04	0.00	0.96	0.05	0.00	0.95
	Dark Gray	Cotton Sateen	0.07	0.00	0.93	0.07	0.00	0.93
	Medium Gray	Cotton Sateen	0.31	0.00	0.69	0.33	0.00	0.67
	Light Gray	Cotton Sateen	0.50	0.06	0.44	0.52	0.06	0.42
	White	Cotton Sateen	0.71	0.15	0.14	0.73	0.12	0.15

DISTRIBUTION LIST NO. 100  
Thermal Radiation Reports  
(Research)

19 July 1956

<u>ADDRESSEE</u>	<u>ARMY</u>	<u>NO. OF COPIES</u>
Assistant Deputy Chief of Staff for Military Operations, Dept. of the Army, Washington 25, D. C. ATTN: Assistant Executive, (RASW)		1
Chief of Research and Development, Dept. of the Army, Washington 25, D. C. ATTN: Atomics Division		1
Chief of Ordnance, Dept. of the Army, Washington 25, D. C. ATTN: ORDTX-AR		1
Chief Signal Officer, Dept. of the Army, Washington 25, D. C. ATTN: SIGOP		3
The Surgeon General, Dept. of the Army, Washington 25, D. C. ATTN: Ch, R&D Div		1
Chief Chemical Officer, Dept. of the Army, Washington 25, D. C.		2
Chief of Engineers, Dept. of the Army, Washington 25, D. C. ATTN: ENGNB		3
Research Branch, Office of Research and Development, The Quartermaster General, Dept. of the Army, Washington 25, D. C.		1
Chief of Transportation, Dept. of the Army, Washington 25, D. C. ATTN: Military Planning & Intelligence Div.		1
Commanding General, Continental Army Command, Ft. Monroe, Va.		4
President, Board #1, Headquarters, Continental Army Command, Ft. Sill, Oklahoma		1
President, Board #2, Headquarters, Continental Army Command, Ft. Knox, Ky.		1
President, Board #4, Headquarters, Continental Army Command, Ft. Bliss, Texas		1

<u>ADDRESSEE</u>	<u>ARMY (Cont'd)</u>	<u>NO. OF COPIES</u>
Commander-in-Chief, FECOM, APO 500, San Francisco, Calif. ATTN: ACofS J-3		2
Commandant, Command & General Staff College, Ft. Leavenworth, Kans. ATTN: ALLS(AS)		1
Commanding General, Army Medical Service School, Brooke Army Medical Center, Ft. Sam Houston, Texas		1
Director, Special Weapons Development Office, Headquarters, Continental Army Command, Ft. Bliss, Texas		1
Commandant, Walter Reed Army Institute of Research, Walter Reed Army Medical Center, Washington 25, D. C. ATTN: Dept. of Biophysics		1
Commandant, Chemical Corps School, Chemical Corps Training Command, Ft. McClellan, Ala.		1
Commanding General, Research & Engineering Command, Army Chemical Center, Md. ATTN: Deputy for RW & Non-Toxic Material		2
Commanding General, The Engineer Center, Ft. Belvoir, Va. ATTN: Ass't. Commandant, Eng School		3
Commanding General, Aberdeen Proving Ground, Aberdeen Proving Ground, Md. ATTN: Director, Ballistics Research Laboratory		2
Commanding Officer, Engineer Research & Development Laboratory, Ft. Belvoir, Va. ATTN: Chief, Tech Intelligence Branch		1
Commanding Officer, Picatinny Arsenal, Dover, N. J. ATTN: ORDBB-TK		1
Commanding Officer, Frankford Arsenal, Philadelphia 37, Pa. ATTN: Col Tewes Kundel		1
Commanding Officer, Army Medical Research Laboratory, Ft. Knox, Ky.		1

<u>ADDRESSEE</u>	<u>ARMY</u> (Cont'd)	<u>NO. OF COPIES</u>
Commanding Officer, Chemical & Radiological Lab., Army Chemical Center, Md. ATTN: Tech Library		2
Commanding Officer, Transportation Command, Ft. Eustis, Va. ATTN: Special Projects Division, Technical Intelligence Branch		1
Director, Technical Documents Center Evans Signal Laboratory, Belmar, N. J.		1
Director, Waterways Experiment Station, P. O. Box 631, Vicksburg, Miss. ATTN: Library		1
Director, Operations Research Office, The Johns Hopkins University, 7100 Connecticut Avenue, Chevy Chase, Md., Washington 15, D. C.		1
Chemical Biological and Radiological Warfare Branch Quartermaster Research & Development Command, Quartermaster Research & Development Center, Natick, Mass.		2

NAVY

Chief of Naval Operations, Dept. of the Navy, Washington 25, D. C. ATTN: OP-36	2
Chief of Naval Operations, Dept. of the Navy, Washington 25, D. C. ATTN: OP-03EG	1
Chief, Bureau of Medicine & Surgery, Dept. of the Navy, Washington 25, D. C. ATTN: Special Weapons Defense Division	1
Chief, Bureau of Ordnance, Dept. of the Navy, Washington 25, D. C.	1
Chief of Naval Personnel, Dept. of the Navy, Washington 25, D. C. ATTN: Pers C-115	1
Chief, Bureau of Ships, Dept. of the Navy, Washington 25, D. C. ATTN: Code 348	2
Code 312	4

<u>ADDRESSEE</u>	<u>NAVY (Cont'd)</u>	<u>NO. OF COPIES</u>
Chief, Bureau of Supplies and Accounts, Dept. of the Navy, Washington 25, D. C.		1
Chief, Bureau of Yards & Docks, Dept. of the Navy, Washington 25, D. C. ATTN: D-440		1
Chief, Bureau of Aeronautics, Dept. of the Navy, Washington 25, D. C.		2
Chief of Naval Research, Dept. of the Navy, Washington 25, D. C. ATTN: Code 811		1
Commander-in-Chief, U. S. Pacific Fleet, FPO, San Francisco, Calif.		1
Commander-in-Chief, U. S. Atlantic Fleet, U. S. Naval Base, Norfolk II, Va.		1
Commandant of the Marine Corps, Dept. of the Navy, Washington 25, D. C. ATTN: Code A03H		4
President, U. S. Naval War College, Newport, R. I.		1
Superintendent, U. S. Naval Postgraduate School, Monterey, Calif.		1
Commanding Officer, U. S. Naval School Command, U. S. Naval Station, Treasure Island, San Francisco, Calif.		2
Commanding Officer, U. S. Fleet Training Center, Naval Base, Norfolk II, Va. ATTN: Special Weapons School		2
Commanding Officer, U. S. Fleet Training Center, Naval Station, San Diego 36, Calif. ATTN: SPWP School		2
Commanding Officer, Air Development Squadron 5, VX-5, U. S. Naval Air Station, Moffett Field, Calif.		1

<u>ADDRESSEE</u>	<u>NAVY (Cont'd)</u>	<u>NO. OF COPIES</u>
Commanding Officer, U. S. Naval Damage Control Training Center, Naval Base, Philadelphia 12, Pa. ATTN: ABC Defense Course		1
Commanding Officer, U. S. Naval Unit, Chemical Corps School, Army Chemical Training Center, Ft. McClellan, Alabama		1
Commander, U. S. Naval Ordnance Laboratory, White Oak, Silver Spring 19, Md. ATTN: EE R		1 1
Commander, U. S. Naval Ordnance Test Station, China Lake, Calif.		1
Commanding Officer, U. S. Naval Medical Research Institute, National Naval Medical Center, Bethesda 14, Md.		1
Director, U. S. Naval Research Laboratory, Washington 25, D. C. ATTN: Code 2029		1
Commander, New York Naval Shipyard, Brooklyn 1, N. Y. ATTN: Director, The Material Laboratory		1
Commanding Officer & Director, U. S. Naval Electronics Laboratory, San Diego, Calif. ATTN: Code 4223		1
Commanding Officer, U. S. Naval Radiological Defense Laboratory, San Francisco 24, Calif. ATTN: Tech Info Div		3
Commander, U. S. Naval Air Development Center, Johnsville, Pa.		1
Commanding Officer, Clothing Supply Office, Code 10-0, 29th Street & 3rd Avenue, Brooklyn 32, N. Y.		1
Commanding Officer, Naval Medical Field Research Laboratory, Camp Lejeune, N. C.		1

<u>ADDRESSEE</u>	<u>AIR FORCE</u>	<u>NO. OF COPIES</u>
Assistant for Atomic Energy, Headquarters, U. S. Air Force, Washington 25, D. C.		1
Director of Operations, Headquarters, U. S. Air Force, Washington 25, D. C. ATTN: Operations Analysis		1
Director of Plans, Headquarters, U. S. Air Force, Washington 25, D. C. ATTN: War Plans Div.		1
Director of Requirements, Headquarters, U. S. Air Force, Washington 25, D. C. ATTN: AFDRQ-SA/M		1
Director of Research & Development, Headquarters, Washington 25, D. C. ATTN: Combat Components Div.		1
Director of Intelligence, Headquarters, U. S. Air Force, Washington 25, D. C. ATTN: AFOIN-182		2
The Surgeon General, Headquarters, U. S. Air Force, Washington 25, D. C. ATTN: Bio Defense Br., Prev Med Division		1
Commander-in-Chief, Strategic Air Command, Offutt AFB, Nebraska ATTN: Chief, Operations Analysis		1
Commander, Tactical Air Command, Langley Air Force Base, Va. ATTN: Doc Sec Branch		1
Commander, Air Defense Command, Ent Air Force Base, Colorado		1
Commander, Air Materiel Command, Wright-Patterson Air Force Base, Ohio		2
Commander, Air Training Command, Scott Air Force Base, Ill. ATTN: DCS/O GTP		1
Commander, Air Research & Development Command, P. O. Box 1395, Baltimore 3, Md. ATTN: RDDN		3
Commander, Air Proving Ground Command, Eglin Air Force Base, Fla. ATTN: AG/TRB		1



<u>ADDRESSEE</u>	<u>AIR FORCE (Cont'd)</u>	<u>NO. OF COPIES</u>
Director, Air University Library, Maxwell Air Force Base, Ala.		2
Commander, Flying Training Air Force, Waco, Texas ATTN: Director of Observer Training		2
Commander, Crew Training Air Force, Randolph Air Force Base, Randolph Field, Tex. ATTN: 2GTS, DCS/O		1
Commander, Technical Training Air Force, Gulfport, Miss. ATTN: TA&D		1
Commander, U. S. Air Force School of Aviation Medicine, Randolph Air Force Base, Randolph Field, Texas		2
Commander, Wright Air Development Center, Wright-Patterson Air Force Base, Ohio ATTN: WCOSI		1
Commander, Air Force Cambridge Research Center, L. G. Hanscom Field, Bedford, Mass. ATTN: CRQST-2		1
Commander, Air Force Special Weapons Center, Kirtland Air Force Base, N. M. ATTN: Technical Information and Intelligence		3
Commander, U. S. Air Force Institute of Technology, Wright-Patterson Air Force Base, Ohio ATTN: Resident College		1
Commander, Lowry Air Force Base, Denver, Colo. ATTN: Dept of Armament Training		1
<u>OTHER DOD ACTIVITIES</u>		
Director, Weapons Systems Evaluation Group, OED, Washington, D. C.		1
Office of the United States National Military Representative - SHAPE, AFM 99, New York, N. Y.		1
Assistant Secretary of Defense, (Research and Development), Washington 25, D. C. ATTN: Tech Library		1
Commandant, Armed Forces Staff College, Norfolk 11, Va. ATTN: Secretary		1

<u>ADDRESSEE</u>	<u>OTHER DOD ACTIVITIES (Cont'd)</u>	<u>NO. OF COPIES</u>
Commander, Field Command, AFSWF, PO Box 5100, Albuquerque, N. M.		6
Chief, Armed Forces Special Weapons Project, Washington 25, D. C.		15
<u>PANEL ON THERMAL RADIATION</u>		
Massachusetts Institute of Technology, Director, Division of Defense Laboratories, Lincoln Laboratory, Cambridge 19, Mass. (For Prof. Hoyt C. Hottel)		1
Dr. Edward O. Hulburt, Senior Scientist, International Geophysical Year, National Academy of Sciences, 2101 Constitution Avenue, N.W., Washington 25, D. C.		1
University of Rochester, Atomic Energy Project, P. O. Box 267, Station 3, Rochester 20, New York ATTN: Tech Report Control Unit (For Dr. Herman E. Pearse)		1
Commander, U. S. Naval Air Development Center, Johnsville, Pa. ATTN: Dr. J. D. Hardy, Aviation Medical Acceleration Lab.		1
<u>OTHERS</u>		
Sandia Corporation, Sandia Base, Albuquerque, New Mexico ATTN: Classified Document Div (For Dr. E. F. COX)		1
Los Alamos Scientific Laboratory, P. O. Box 1663, Los Alamos, N. M. ATTN: Report Librarian (For Dr. Alvin C. Graves, J-Division)		1
Los Alamos Scientific Laboratory, P. O. Box 1663, Los Alamos, N. M. ATTN: Report Librarian		1
Technical Operations, Inc., 2000 P St., N.W., Rm 511, Washington 6, D.C. ATTN: Security Officer (For Mr. Greestone)		1
Medical College of Virginia, Box 222, Richmond, Va. ATTN: Maj. Gen. W. F. Tomkins (For Dr. William T. Ham)		1

ADDRESSEE

OTHERS (Cont'd)

NO. OF COPIES

Director, California Forest and Range Experimental Station,  
U. S. Forest Service,  
P. O. Box 245,  
Berkeley, Calif.  
ATTN: W. L. Fons, Div. of Forest Fire Research

1

Massachusetts Institute of Technology,  
Director, Division of Defense Labs,  
Lincoln Lab,  
Cambridge 19, Mass.  
(For Prof. G. C. Williams)

1

Mr. H. D. Bruce,  
Forest Products Lab.,  
North Walnut Street,  
Madison 5, Wisconsin

1

Chief, Fire Research Division,  
Forest Service,  
U. S. Department of Agriculture,  
Washington 25, D. C.  
ATTN: Mr. A. A. Brown

1

<p>Naval Material Laboratory, New York Naval Shipyard, 5046-3, Part 91</p> <p>RESEARCH REPORT ON THE SPECTRAL REFLECTANCE AND TRANSMITTANCE OF STANDARD FABRICS THERMAL RADIATION EFFECTS STUDIES by T. I. Monahan, G. P. delahery and W. Derksen, Final Report, 28 Aug 1956, 7 p. Tables. (AFSHP 957)</p> <p>UNCLASSIFIED</p> <p>The spectral reflectance and transmittance of standard fabrics for thermal radiation effect studies and two olive green uniform fabrics were measured. The reflectance transmittance and absorbance for carbon arc and 3000 K black-body radiant energy were calculated. The darker gray fabrics were essentially neutral, the lighter shades and the uniform fabrics were not.</p> <p>UNCLASSIFIED</p> <ol style="list-style-type: none"> <li>1. Cotton textiles - Optical properties</li> <li>2. Cotton textiles - Effects of radiation</li> <li>I. delahery, G. P.</li> <li>II. Derksen, W. L.</li> <li>III. Monahan, T. I.</li> <li>IV. NS 081-001</li> <li>V. AFSHP 957</li> </ol>	<p>Naval Material Laboratory, New York Naval Shipyard, 5046-3, Part 91</p> <p>RESEARCH REPORT ON THE SPECTRAL REFLECTANCE AND TRANSMITTANCE OF STANDARD FABRICS THERMAL RADIATION EFFECTS STUDIES by T. I. Monahan, G. P. delahery and W. Derksen, Final Report, 28 Aug 1956, 7 p. Tables. (AFSHP 957)</p> <p>UNCLASSIFIED</p> <p>The spectral reflectance and transmittance of standard fabrics for thermal radiation effect studies and two olive green uniform fabrics were measured. The reflectance transmittance and absorbance for carbon arc and 3000 K black-body radiant energy were calculated. The darker gray fabrics were essentially neutral, the lighter shades and the uniform fabrics were not.</p> <p>UNCLASSIFIED</p> <ol style="list-style-type: none"> <li>1. Cotton textiles - Optical properties</li> <li>2. Cotton textiles - Effects of radiation</li> <li>I. delahery, G. P.</li> <li>II. Derksen, W. L.</li> <li>III. Monahan, T. I.</li> <li>IV. NS 081-001</li> <li>V. AFSHP 957</li> </ol>
<p>Naval Material Laboratory, New York Naval Shipyard, 5046-3, Part 91</p> <p>RESEARCH REPORT ON THE SPECTRAL REFLECTANCE AND TRANSMITTANCE OF STANDARD FABRICS THERMAL RADIATION EFFECTS STUDIES by T. I. Monahan, G. P. delahery and W. Derksen, Final Report, 28 Aug 1956, 7 p. Tables. (AFSHP 957)</p> <p>UNCLASSIFIED</p> <p>The spectral reflectance and transmittance of standard fabrics for thermal radiation effect studies and two olive green uniform fabrics were measured. The reflectance transmittance and absorbance for carbon arc and 3000 K black-body radiant energy were calculated. The darker gray fabrics were essentially neutral, the lighter shades and the uniform fabrics were not.</p> <p>UNCLASSIFIED</p> <ol style="list-style-type: none"> <li>1. Cotton textiles - Optical properties</li> <li>2. Cotton textiles - Effects of radiation</li> <li>I. delahery, G. P.</li> <li>II. Derksen, W. L.</li> <li>III. Monahan, T. I.</li> <li>IV. NS 081-001</li> <li>V. AFSHP 957</li> </ol>	<p>Naval Material Laboratory, New York Naval Shipyard, 5046-3, Part 91</p> <p>RESEARCH REPORT ON THE SPECTRAL REFLECTANCE AND TRANSMITTANCE OF STANDARD FABRICS THERMAL RADIATION EFFECTS STUDIES by T. I. Monahan, G. P. delahery and W. Derksen, Final Report, 28 Aug 1956, 7 p. Tables. (AFSHP 957)</p> <p>UNCLASSIFIED</p> <p>The spectral reflectance and transmittance of standard fabrics for thermal radiation effect studies and two olive green uniform fabrics were measured. The reflectance transmittance and absorbance for carbon arc and 3000 K black-body radiant energy were calculated. The darker gray fabrics were essentially neutral, the lighter shades and the uniform fabrics were not.</p> <p>UNCLASSIFIED</p> <ol style="list-style-type: none"> <li>1. Cotton textiles - Optical properties</li> <li>2. Cotton textiles - Effects of radiation</li> <li>I. delahery, G. P.</li> <li>II. Derksen, W. L.</li> <li>III. Monahan, T. I.</li> <li>IV. NS 081-001</li> <li>V. AFSHP 957</li> </ol>